

ARMONIA Nm 2/28

Composizione

53% (LI) Lino / 47% (WV) Lana Merino Extrafine RWS

Impiego 2/28

Rettilezza fin. 10-12 / Cotton 21 gg

Oeko-tex standard 100

Consigli per il finissaggio

È sufficiente abbondante vaporizzo libero in fase di stiro. Per avere una mano più morbida, si possono lavare delicatamente le maglie rovesciate a 30°C per due minuti con detergente neutro. Stirare con vapore.

Importante

All'inizio di ogni bagno controllare attentamente i primi teli smacchinati, in caso di imperfezioni, interrompere la smacchinatura avvisando il servizio commerciale Filivivi. Nel caso il filato abbia prolungati periodi di giacenza in magazzino è buona norma sottoporlo ad una nuova paraffinatura. Tale operazione è consigliabile anche nel caso di lavorazioni particolari.

Solidità colori

- Secondo norme Woolmark (TM193 - TM165 - TM5)
- Solidità colori garantite (solidità speciali, articoli sportivi e rigature, su richiesta)

Simboli di manutenzione / Care symbols



ARMONIA Nm 2/28

Composition

53% (LI) Linen / 47% (WV) Extrafine Merino Wool RWS

Knitting 2/28

Flat machine 10-12 / Cotton 21 gg

Oeko-tex standard 100

Finishing suggestions

An abundant and free steam is necessary during ironing. In order to obtain soft touch, wash delicately inside-out at 30°C for 2 minutes using neutral detergents.
Iron with steam.

Important

Before knitting each dyelot please check carefully the first knitted swatches and in the case of some faulty yarn stop knitting and inform the commercial service of Filivivi.
In cases the yarn has been stored for long periods of time, it is advisable to rewax it. This is also advisable in the case of special manufacturing.

Colour fastness

- In accordance with Woolmark Standards (TM193 - TM165 - TM5)
- Colour fastness (special colour fastness, sportswear and stripes, upon request)

Certificazioni / Certifications



Filivivi Srl con Socio Unico is RWS certified
By ICEA
ICEA-TX- 107

"Only the products which are covered by a valid Transaction certificate are RWS certified"